



# Standard Specification for Carbon Steel Forgings for Piping Components with Inherent Notch Toughness<sup>1</sup>

This standard is issued under the fixed designation A727/A727M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers forged carbon steel piping components intended primarily for service in pressure piping systems from –20 to +650 °F [–30 to +345 °C] where inherent notch toughness is desired, but where notch toughness testing is not required. Included are forged or ring-rolled flanges, forged fittings, and valves made to specified dimensions, or to dimensional standards such as the ASME and API specifications referenced in Section 2.

1.2 This specification is limited to forgings with maximum finished section thicknesses no larger than 2 in. [51 mm].

1.3 It shall be the responsibility of the purchaser to determine whether material meeting the requirements of this specification is satisfactory for the service application.

1.4 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified by the purchaser in the order.

NOTE 1—There are no provisions for impact testing in this specification. When impact testing is required, refer to Specification A350/A350M.

1.5 This specification is expressed in both inch-pound units and in SI units. However, unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished to inch-pound units.

1.6 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system

shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

## 2. Referenced Documents

2.1 In addition to those reference documents listed in Specification A961/A961M, the following list of standards apply to this specification.

### 2.2 ASTM Standards:<sup>3</sup>

A350/A350M Specification for Carbon and Low-Alloy Steel Forgings, Requiring Notch Toughness Testing for Piping Components

A788/A788M Specification for Steel forgings, General Requirements

A961/A961M Specification for Common Requirements for Steel Flanges, Forged Fittings, Valves, and Parts for Piping Applications

E59 Practice for Sampling Steel and Iron for Determination of Chemical Composition (Withdrawn 1996)<sup>4</sup>

### 2.3 ASME Boiler and Pressure Vessel Codes:<sup>5</sup>

Section II, Material Specifications, Part C

SFA 5.5 Low-Alloy Steel Covered Arc-Welding Electrodes

B 16.5 Steel Pipe Flanges and Flanged Fittings

B 16.10 Face-to-Face and End-to-End Dimensions of Ferrous Valves

B 16.11 Forged Steel Fittings, Socket-Welding and Threaded

B 16.30 Unfired Pressure Vessel Flange Dimensions

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved Oct. 1, 2014. Published October 2014. Originally approved in 1976. Last previous edition approved in 2013 as A727/A727M-13. DOI: 10.1520/A0727\_A0727M-14.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-727 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>5</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, http://www.asme.org.

## 2.4 API Standards:<sup>6</sup>

- 600 Steel Gate Valves with Flanged or Butt-Welding Ends**
- 602 Compact Design Carbon Steel Gate Valves for Refinery Use**
- 605 Large Diameter Carbon Steel Flanges**

## 2.5 MSS Standard:<sup>7</sup>

- MSS SP-25 Standard Marking System for Valves, Fittings, Flanges, and Unions**

## 3. General Requirements and Ordering Information

3.1 Product furnished to this specification shall conform to the requirements of Specification **A961/A961M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the requirements of Specification **A961/A961M** constitutes nonconformance with this specification. In case of a conflict between the requirements of this specification and Specification **A961/A961M**, this specification shall prevail.

3.2 It is the purchaser's responsibility to specify in the purchase order all ordering information necessary to purchase the needed material. Examples of such information include but are not limited to the following:

- 3.2.1 Additional requirements (see **16.1**).

## 4. Materials and Manufacture

4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace, and shall be fully killed, fine-grain practice.

4.2 forgings shall be manufactured from ingots, blooms, billets, slabs, or bars. These items shall be forged, rolled, or strandcast.

4.3 A sufficient discard shall be made from the ingot to secure freedom from injurious piping and undue segregation.

4.4 The finished product shall be a forging as defined by the Terminology section of Specification **A788/A788M**.

## 5. Heat Treatment

5.1 Following plastic working, the forging manufacturer shall heat treat the forgings by normalizing, or normalizing and tempering, or quenching and tempering.

5.1.1 *Normalizing*—The procedure for normalizing shall consist of uniformly heating the forgings to a temperature between 1550 and 1700 °F [845 and 925 °C], holding a sufficient time to attain uniform temperature throughout, and cooling in still air. The forging shall be at a temperature below 1000 °F [540 °C] before heating for normalizing.

5.1.2 *Quenching*—The procedure for quenching shall consist of uniformly heating the forging to a temperature between 1550 and 1700 °F [845 and 925 °C], holding a sufficient time to attain uniform temperature throughout, and quenching into a

suitable liquid medium. The forging shall be at a temperature below 1000 °F [540 °C] before heating for quenching.

5.1.3 *Tempering*—The procedure for tempering shall consist of reheating the forging subsequent to normalizing or quenching to a temperature of at least 1100 °F [595 °C], but not above the lower transformation temperature, for 30 min/in. [30 min/25 mm] of maximum section thickness, with minimum holding time at tempering temperature not less than 30 min.

## 6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 1**.

6.2 Steels to which lead has been added shall not be used.

## 7. Mechanical Requirements

### 7.1 Tension Tests:

7.1.1 *Requirements*—The material shall conform to requirements for tensile properties prescribed in **Table 2**.

7.1.1.1 The test specimen shall be obtained from a rough or finished production forging, or prolongation thereof, or it may be obtained from separately forged test blanks from the same heat of steel as the production forging. The test blank shall be reduced by forging in a manner similar to that for the products represented, shall receive approximately the same hot working and reduction, be of the same nominal thickness, and receive the same heat treatment as the finished products represented.

**TABLE 1 Chemical Requirements**

Elements	Composition, %
Carbon	
Heat Analysis	0.25 max
Product Analysis	0.28 max
Manganese	
Heat Analysis	0.90 to 1.35
Product Analysis	0.84 to 1.41
Phosphorus	
Heat Analysis	0.035 max
Product Analysis	0.043 max
Sulfur	
Heat Analysis	0.025 max
Product Analysis	0.033 max
Silicon	
Heat Analysis	0.15 to 0.30
Product Analysis	0.13 to 0.32
Nickel	
Heat Analysis	0.40 <sup>A</sup>
Product Analysis	0.43
Chromium	
Heat Analysis	0.30 <sup>A,B</sup>
Product Analysis	0.34
Molybdenum	
Heat Analysis	0.12 <sup>A,B</sup>
Product Analysis	0.13
Copper	
Heat Analysis	0.40 <sup>A</sup>
Product Analysis	0.43
Columbium (Nb)	
Heat Analysis	0.02
Product Analysis	0.03
Vanadium	
Heat Analysis	0.05
Product Analysis	0.055

<sup>A</sup> The sum of copper, nickel, chromium and molybdenum shall not exceed 1.00 % on heat analysis.

<sup>B</sup> The sum of chromium and molybdenum shall not exceed 0.32 % on heat analysis.

<sup>6</sup> Available from American Petroleum Institute (API), 1220 L. St., NW, Washington, DC 20005-4070, <http://api-ec.api.org>.

<sup>7</sup> Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

**TABLE 2 Tensile Requirements**

Tensile strength, ksi [MPa]	60.0 to 85.0 [415 to 585]
Yield strength, min, ksi [MPa] <sup>a</sup>	36.0 [250]
Elongation in 2 in. or 50 mm, min, %	22
Reduction of area, min, %	30

<sup>a</sup> Determined by either the 0.2 % offset method or the 0.5 % extension-under-load method.

The test material shall be treated in the same furnace at the same time as the forging it represents, subject to the requirements of 7.1.2.1.

7.1.2 *Number of Tests*—One tension test at room temperature shall be made for each nominal wall thickness  $\pm \frac{1}{4}$  in. [ $\pm 6$  mm] from each heat in each heat treatment charge.

7.1.2.1 If heat treatment is performed in either a continuous or a batch-type furnace controlled within  $\pm 25$  °F [ $\pm 14$  °C] of the required heat-treatment temperature, and equipped with recording pyrometers so that complete records of heat treatment are available and if the same heat treating cycles are used on the forgings represented by the tension test, then one tension test per nominal wall thickness  $\pm \frac{1}{4}$  in. [ $\pm 6$  mm] from each heat shall be required, instead of one tension test per nominal wall thickness from each heat in each heat-treatment charge.

7.1.3 *Test Locations and Orientations*—The test specimen shall be removed from the midwall of the heaviest section of the forging or test blank.

7.1.3.1 The test specimen shall have its longitudinal axis located parallel to the direction of major working of the forging or test blank, except for flanges and rings the test specimen shall be in the tangential direction.

7.1.4 *Test Method*—Testing shall be performed as specified in Specification A961/A961M using the largest feasible of the round specimens.

### 7.2 Hardness Test:

7.2.1 *Requirements*—If the production forgings are liquid-quenched and tempered, hardness of the forgings shall not exceed 187 HBW after heat treatment. The purchaser may verify that the requirement has been met by testing at any location on the forgings provided such testing does not render the forgings useless.

## 8. Heat Analysis

8.1 An analysis of each heat of steel shall be made from samples taken preferably during the pouring of the heat. The results shall conform to Table 1.

## 9. Product Analysis

9.1 A product analysis may be made by the purchaser on samples taken in accordance with Practice E59. The results shall conform to Table 1.

## 10. Hydrostatic Test

10.1 Forgings manufactured under this specification shall be capable of passing a hydrostatic test compatible with the rating of the finished forging. Such tests shall be conducted by the forging manufacturer only when Supplementary Requirement S8 in Specification A961/A961M is specified.

## 11. Rework and Retreatment

11.1 If the results of mechanical tests do not conform to the requirements specified, the manufacturer may reheat treat the forgings represented, and shall retest to the applicable requirements.

11.2 Individually tested forgings meeting all requirements shall be acceptable.

## 12. Surface Finish, Appearance, and Corrosion Protection

12.1 The requirements of Specification A961/A961M apply to forgings and finished parts.

## 13. Repair by Welding

13.1 Repair of defects by welding shall be permitted at the discretion of the forging manufacturer.

13.2 Repair by welding shall be made using welding procedures and welders qualified in accordance with Section IX of the ASME Boiler and Pressure Vessel Code. When forgings are heat treated after repair welding, the qualification test plates shall be subjected to the same heat treatment. The mechanical properties of the qualification test plates shall conform to Section 7.

13.3 Only electrode classifications with the -A1 designator shall be used (for example, E71T1-A1). SMAW, GMAW, FCAW or GTAW may be used. The GMAW process is limited to either the spray transfer or pulsed arc process. The FCAW process is limited to repair of carbon or carbon-molybdenum base materials only. Electrodes shall conform to the applicable AWS A5 electrode specification.

13.4 Forgings repair welded in the normalized, normalized and tempered, or the quenched and tempered conditions shall be stress-relieved after repair welding at 1100 °F [595 °C] minimum, but not higher than the temperature previously used for tempering the base metal of the same forging, or shall be reheat treated in accordance with Section 5.

## 14. Inspection

14.1 All tests and inspections shall be made at the place of manufacture, unless otherwise agreed, except for product analysis (see 9.1).

## 15. Rejection and Rehearing

15.1 Each forging that develops injurious defects during shop working or application shall be rejected and the manufacturer notified.

## 16. Certification

16.1 In addition to the certification requirements of Specification A961/A961M, test reports shall be furnished to the purchaser or his representative. Test reports shall provide the following where applicable:

16.1.1 Type heat treatment, Section 5,

16.1.2 Chemical analysis results, Section 6, (Table 1), reported results shall be to the same number of significant figures as the limits specified in Table 1 for that element,



- 16.1.3 Product analysis results, Section 9 (**Table 1**),
- 16.1.4 Tensile properties results, Section 7 (**Table 2**), report the yield strength and tensile strength in ksi [MPa], and elongation and reduction of area in percent,
- 16.1.5 Hardness results, **7.2**, and
- 16.1.6 Any supplementary testing required by the purchase order.

## 17. Product Marking

- 17.1 In addition to marking requirements of Specification **A961/A961M**, the following additional marking requirements shall apply:

17.1.1 If the forgings have been quenched and tempered the letters "QT" shall be stamped on the forgings following the Specification designation.

17.1.2 forgings repaired by welding shall be marked with the letter "W" following the specification designation.

17.2 *Bar Coding*—In addition to the requirements in 17.1, bar coding is acceptable as a supplemental identification method. The purchaser may specify in the order a specific bar coding system to be used. The bar coding system, if applied at the discretion of the supplier, should be consistent with one of the published industry standards for bar coding. If used on small parts, the bar code may be applied to the box or a substantially applied tag.

## 18. Keywords

18.1 carbon equivalent; pipe fittings; steel; piping applications; pressure containing parts; steel flanges; steel forgings; carbon; steel valves; temperature service applications; low

## SUPPLEMENTARY REQUIREMENTS

One or more of the following supplementary requirements shall be applied only when specified by the purchaser in the inquiry, contract, or order. Details of these supplementary requirements shall be agreed upon in writing by the manufacturer and purchaser. Supplementary requirements shall in no way negate any requirement of the specification.

### S1. Carbon Equivalent

S1.1 The maximum carbon equivalent, based on heat analysis shall be 0.45 for forgings with a maximum section thickness of 2 in. or less, and 0.46 for forgings with a maximum section thickness of greater than 2 in.

S1.2 Determine the carbon equivalent (CE) as follows:

$$\text{CE} = \text{C} + \text{Mn}/6 + (\text{Cr} + \text{Mo} + \text{V})/5 + (\text{Ni} + \text{Cu})/15$$

S1.3 A lower maximum carbon equivalent may be agreed upon between the supplier and the purchaser.

## SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this specification since the last issue, A727/A727M–13, that may impact the use of this specification. (Approved October 1, 2014)

(I) Added Section 12 on surface finish, appearance, and corrosion protection.

Committee A01 has identified the location of selected changes to this specification since the last issue, A727/A727M–11, that may impact the use of this specification. (Approved October 1, 2013)

(I) Revised Sections 16 and 17 on certification and marking.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*